

ALDASA URBAN EX

Coating for Outdoors

Aldasa Urban EX is a two-component continuous coating with two components (A in powder + B resin) formulated with hydraulic binders, synthetic resins, specific additives and selected colorants.

As part of an application system the surface should be prepared with **Aldasa Base EX** and products recommended by **decóra cement®**.

Once mixed, the product obtained can create a thin coating, with high mechanical resistance and strong grip on any type of substrate: concrete, cement-based mortars, ceramic, MDF, plaster and drywall, as long as they are correctly prepared.

Properties:

- Continuous decorative coating without fissures (do always respect the expansion joints).
- Applicable on countless surfaces: concrete, cement, ceramic, plasterboard, etc.
- Excellent workability.
- Wide range of colours.
- Finishes: matt, satin and gloss.
- High adhesion to substrates.
- More mechanical strength and abrasion resistance than Microdeck.
- Slip resistant properties without any additional anti-slip treatment.

Instructions for application:

a. Surface preparation:

It is necessary to prepare the surface with **Aldasa Base EX** before applying **Aldasa Urban EX**. The surface should be free of dust and grease, well consolidated and in good flatness.

b. Mix:

Add Acricem resin and pigments in the recommended proportions. It is essential to respect the resin-microcement ratio to ensure the product properties:

10kg Aldasa Urban EX – 2.7 litres of resin

c. Mortar preparation:

The mortar must be prepared as follows:

1. Pour some resin in a container; then add the entire load of pigment corresponding to the amount of microcement and mix until an even, coloured liquid is obtained.
2. Pour the microcement powder gradually into the resin while mixing the product with a low speed mixing drill.
3. Mix at least 4 minutes until a smooth mixture free of lumps is obtained.

d. Consumption:

The consumption depends on the surface. In a standard application it would be as follows:

Aldasa Urban EX (2 layers) – 0.5 kg/m²

The better the levelling and preparation of the surface to be coated, the better the performance and the lower the time of installation. It is advisable to choose the suitable method for each application.

Technical data:

Type:	Two component microcement
Appearance:	White powder
Maximum size of the aggregates:	0.40 mm
Apparent density:	In powder – 1175 ± 50kg/m ³
	In mortar – 1480 ± 50kg/m ³
	Hardened – 1430 ± 50kg/m ³ (28 days)
Compressive strength (EN 13892-2):	28 days: > 50 N/mm ²
Flexural strength (EN 13892-2):	28 days: > 11 N/mm ²
Adhesion strength (EN 13892-8):	28 days: > 1.5 N/mm ²
Slip resistance (EN 12633:2003):	USRV Rd = 55 Class 3
Fire resistance (EN 13501-1):	B _{FL} s1

Application:

a. Preparation or rendering layer:

Apply one layer of **Aldasa Base EX** with a steel trowel. Always install the flexible fibreglass **Mesh** on floors. Apply two layers of **Aldasa Urban EX** with a flexible steel trowel. Before applying a new layer, let dry the last one and sand smoothly with a random orbital sander and 40-grit sandpapers to remove imperfections.

b. Finishing or setting coat:

Apply two layers of **Aldasa Urban EX** with a flexible steel trowel using one of these techniques:

“Fresh on fresh”

Aldasa Urban EX can be applied with the “fresh on fresh” by installing a layer as soon as the previous one is tack-free (non-sticky to the touch). No sanding is required for the first **Aldasa Urban EX** layer when using this technique. Should you find burrs or bumps, smooth them out with a spatula and cut the rough edges. Work on an extruded polystyrene board to apply the following layer. Sand the surface Sand lightly with a random orbital sander 40-grit sandpaper gloves to remove imperfections once the material has dried-once the colour tone changes and intensity becomes lighter.

“Fresh on dry”

A layer is applied once the previous one has dried in about 3 hours. Then sand lightly with a random orbital sander or 40-grit sandpaper gloves to remove imperfections.

We recommend a total thickness of the combined layers of 4 mm.

c. Sealing:

decóra cement® microcements should be sealed once they have hardened, after 24 - 48 hours. Sealing shall be done after the coating reaches humidity lower than 5%, measured with tools designed for this purpose. **decóra cement**® microcements can be sealed with primer **Aldasa Varnish EX** and water-based varnish **Aldasa Polyurethane EX (A+B)** We highly recommend carefully following the installation instructions of technical datasheet.

Special precautions:

This product contains cement.

- Avoid contact with eyes and skin, as well as powder inhalation.
- Use rubber gloves and safety glasses.
- Apply this product at ambient temperature between 10°C and 30°C. Both low and high temperatures might vary the pot life and drying times considerably.

Empty containers must be disposed of in accordance with current local regulations.

Keep out of the reach of children.

**Usage:**

Mortar for coating indoors or outdoors walls and floors, dry and wet areas of both residential and commercial spaces.

Packing:

Available in 20 kg buckets.

Cleaning tools:

Tools should be cleaned with water immediately after use. Once the material has hardened, it can only be removed by mechanical means.

Pot life:

The pot life is 1 hour at about 20°C.

It is advisable to mix quantities in accordance with the experience of the installer.

Storage conditions:

decóra cement microcement should be stored in its closed original packaging, protected from weather conditions and at temperatures below 30 °C. Resin must be stored in closed original packaging protected from weather conditions and always between 10°C and 30°C. Shelf life is about 12 months from date of production if stored in well-preserved conditions.

The product should not be used for purposes other than those specified without first having instructions in writing. It is always the user's responsibility to take suitable measures in order to comply with the requirements established in local legislation. Product safety sheets are available for professionals. This technical data sheet will be valid until a new edition appears.

decóra
cement